



Desmopan 955 U

900 grade series, ether / Shore hardness D 55 - 59

Extrusion- and injection molding grade; with special UV stabilizers; very good hydrolysis and microbial resistance; very good low-temperature impact strength; Application; Ski boot shells; Hoses, non-reinforced; Injection molded engineering parts

ISO Shortname

Property	Test Condition	Unit	Standard	Value		
				drying	annealed	-
Mechanical properties (23 °C/50 % r. h.)						
C shore hardness, method A		-	ISO 868			97
C shore hardness, method D		-	ISO 868			55
C Ultimate tensile strength	200 mm/min	MPa	b.o. ISO 527-1,-3			55
C Strain at break	200 mm/min	%	b.o. ISO 527-1,-3			400
C Stress at 100 % strain	200 mm/min	MPa	b.o. ISO 527-1,-3			20
C Stress at 300 % strain	200 mm/min	MPa	b.o. ISO 527-1,-3			35
C Compression set	24 h; 70 °C	%	ISO 815			56
C Compression set	72 h; 23 °C	%	ISO 815			38
C Abrasion resistance		mm ³	ISO 4649			40
Impact resilience		%	ISO 4662			38
Tear propagation resistance	500 mm/min	kN/m	ISO 34-1			140
Flexural modulus	2 mm/min	MPa	ISO 178			170
Thermal properties						
Torsional storage modulus	-20 °C	MPa	ISO 6721-2			330
Torsional storage modulus	23 °C	MPa	ISO 6721-2			104
Torsional storage modulus	70 °C	MPa	ISO 6721-2			32
Tensile storage modulus	-20 °C	MPa	ISO 6721-1,-4			1080
Tensile storage modulus	20 °C	MPa	ISO 6721-1,-4			371
Tensile storage modulus	60 °C	MPa	ISO 6721-1,-4			48
Other properties (23 °C)						
C Density		kg/m ³	ISO 1183			1160
Molding conditions						
Injection molding-Melt temperature		°C	-	215 - 235		
Injection molding-Mold temperature		°C	-			20 - 40
Extrusion-Melt temperature		°C	-	205 - 235		
Maximum drying temperature		°C	-			110

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break



Desmopan 955 U

Disclaimer

Disclaimer for Sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardized test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Please note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mold/die, the processing conditions and coloring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded.

Disclaimer

All of the information, documents and illustrations published on this website are the exclusive property of BAYER. Permission for their use is given on the proviso that the copyright note appears on all copies, that only personal and not commercial use is made of the information, that the information is not altered in any way and that all illustrations on the website are used only in conjunction with the associated texts. BAYER assumes no liability or warranties with respect to the information, documents and illustrations on the website. BAYER is not responsible for any damage of whatever nature that might arise from the use or existence of the website and the information, documents and illustrations it contains. The user bears full responsibility for all risks to him that might arise from the use of this website. BAYER reserves the right to amend or supplement the documents and information provided on the website at any time and without prior notice. The user of this website is fully responsible for the content and correctness of details he or she sends to BAYER, as well as for non-violation of any third-party rights that may be involved in such details.

Publisher: Global Innovations - Polycarbonates

Bayer MaterialScience AG,

D-51368 Leverkusen,

www.bayermaterialscience.com