

# Texin 4210

/ Thermoplastic polyurethane/polycarbonate blend for injection molding and extrusion.

## ISO Shortname

Property	Test Condition	Unit	Standard	Value
<b>Rheological properties</b>				
Mold shrinkage, flow/cross to flow	Value range based on general practical experience	in/in	ASTM D955	0.008
<b>Mechanical properties (23 °C/50 % r. h.)</b>				
Flexural modulus	73 °F	lb/in <sup>2</sup>	ASTM D790	100000
Izod notched impact strength	73 °F; 0.125 in	ft·lb/in	ASTM D256	16
Izod notched impact strength	-22 °F; 0.125 in	ft·lb/in	ASTM D256	1
Instrumented impact, Peak energy	73 °F; 0.100 in; 0.5-in dart; 1.6-in clamp; 7.6 mph	ft·lb	ASTM D3763	35.8
Instrumented impact, Peak energy	-22 °F; 0.100 in; 0.5-in dart; 3-in clamp; 7.6 mph	ft·lb	ASTM D3763	40.5
Shear strength		ft·lb/in <sup>2</sup>	ASTM D732	6200
Tensile strength		lb/in <sup>2</sup>	ASTM D412	6000
Ultimate elongation		%	ASTM D412	180
Tear strength, Die C		lbf/in	ASTM D624	900
<b>Thermal properties</b>				
Glass transition temperature	DMA=Dynamic Mechanical Analysis	°F	DMA	-31
Low-temperature brittle point		°F	ASTM D746	< -90
Deflection temperature under load	66 psi	°F	ASTM D648	208
Deflection temperature under load	264 psi	°F	ASTM D648	139
Vicat softening temperature	Rate A; 1 kg; 50 °C/h	°F	ASTM D1525	282
Coefficient of linear thermal expansion, flow/cross-flow		in/in/°F	ASTM D696	5.7E-5
<b>Other properties (23 °C)</b>				
Specific gravity		-	ASTM D792	1.21
Shore hardness		D Scale	ASTM D2240	70
Taber abrasion	H-18 wheel; 1,000-g; 1,000 cycles	mg Loss	ASTM D3489	65
Bayshore resilience		%	ASTM D2632	45

# Texin 4210

---

## Disclaimer

Publisher: Global Innovations - Polycarbonates  
Bayer MaterialScience AG,  
D-51368 Leverkusen,  
[www.bayermaterialscience.com](http://www.bayermaterialscience.com)

---

Page 2 of 2 pages

Edition 04.02.2010

**Texin<sup>®</sup>**  
ASTM Datasheet