

Texin 985 U

/ Polyether-based UV stabilized grade with Shore A hardness of approximately 86 for injection molding and extrusion.

ISO Shortname

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Mold shrinkage, flow/cross to flow	Value range based on general practical experience	in/in	ASTM D955	0.008
Mechanical properties (23 °C/50 % r. h.)				
Flexural modulus	73 °F	lb/in ²	ASTM D790	3900
Flexural modulus	-22 °F	lb/in ²	ASTM D790	8560
Tensile strength		lb/in ²	ASTM D412	5500
Ultimate elongation		%	ASTM D412	500
Tensile stress at 50 % elongation		lb/in ²	ASTM D412	700
Tensile stress at 100 % elongation		lb/in ²	ASTM D412	800
Tensile stress at 300 % elongation		lb/in ²	ASTM D412	1200
Compression set, as molded	22 h at 73 °F	%	ASTM D395-B	19
Compression set, as molded	22 h at 158 °F	%	ASTM D395-B	80
Compression set, post-cured	22 h at 73 °F; post-cured 16 h at 230 °F	%	ASTM D395-B	16
Compression set, post-cured	22 h at 158 °F; post-cured 16 h at 230 °F	%	ASTM D395-B	40
Compressive load	2% deflection	lb/in ²	ASTM D575	50
Compressive load	5% deflection	lb/in ²	ASTM D575	150
Compressive load	10% deflection	lb/in ²	ASTM D575	300
Compressive load	15% deflection	lb/in ²	ASTM D575	450
Compressive load	20% deflection	lb/in ²	ASTM D575	625
Compressive load	25% deflection	lb/in ²	ASTM D575	800
Compressive load	50% deflection	lb/in ²	ASTM D575	2400
Tear strength, Die C		lbf/in	ASTM D624	500
Thermal properties				
Glass transition temperature	DMA=Dynamic Mechanical Analysis	°F	DMA	-51
Low-temperature brittle point		°F	ASTM D746	< -90
Vicat softening temperature	Rate A; 1 kg; 50 °C/h	°F	ASTM D1525	176
Other properties (23 °C)				
Specific gravity		-	ASTM D792	1.12
Shore hardness		A Scale	ASTM D2240	85
Taber abrasion	H-18 wheel; 1,000-g; 1,000 cycles	mg Loss	ASTM D3489	30
Bayshore resilience		%	ASTM D2632	45

Texin 985 U

Disclaimer

Publisher: Global Innovations - Polycarbonates
Bayer MaterialScience AG,
D-51368 Leverkusen,
www.bayermaterialscience.com